

BONEdry EM COATING

Specifications

Description

Bone Dry EM (epoxy modified) Coating is a durable, spray applied, 2-part epoxy modified surface coating with excellent chemical resistance to common warehouse fluids, gasoline, anti-freeze, brake fluid, solvents, salts, acetone, and alcohol. Bone Dry EM Coating's durability will withstand scratching, forklift traffic, and bonds to concrete and existing sealers.

Testing

- FDA 177.1390: Approval for direct contact with food
- Hot Seal Test: 446 F at 45psi- pass
- Pencil Hardness: greater than 6H
- Shore D Hardness: 80
- Konig (Pendulum)- 163 seconds
- Chemical Resistance: 150 Double Rubs
 - MEK: Pass
 - Acetone: Pass
 - Isopropyl Alcohol: Pass
- Contains NO polyisocyanate

Slip Resistance

Bone Dry EM Coating conforms to the texture of the surface which it is applied providing little to no reduction in slip resistance.

Concrete Floor Preparation

Remodeled Surfaces

Clean the existing surface to remove any loose debris and cracking or peeling coatings. Existing surface must be dry and free of moisture ingress.

Newly Cured Concrete Surfaces

Allow the new concrete slab to cure for 28 days prior to application. Remove any existing dust and debris. Existing slab must be dry and free of moisture ingress.

Protection/Equipment

Protecting Finished Surfaces

Mask off any finishes prior to applying product. Dried product will be difficult to remove. Refer to individual product SDS for handling.

Equipment for Application

Bone Dry EM Coating can be applied using a pump sprayer, battery powered sprayer, mop, "wet" microfiber pad, lambs wool pad, or roller.

Mixing

Mix the coupling agent into Bone Dry EM Coating and stir with an electric drill mixing paddle for 3-5 minutes.

Pot Life: 2 hours

Application

Apply one coating to the existing surface. Allow the product to dry for 48 hours prior to allowing foot traffic. Allow the product to cure 72 hours before allowing vehicle traffic.

- Orange peel finish- apply using a pump or battery powered sprayer.
- Smooth finish- apply using a microfiber pad, lambs wool pad, or roller

Cure time: 72 hours

Spread Rate: 300-350 sqft per gal.

Cleanup:

Remove uncured material with running water and scrub as needed.

Storage

Store unmixed product in a conditioned space where temperatures range between 35-90 F. Do not freeze.

Warranty Information

Bone Dry EM Coating carries a manufacturer's limited warranty stating that this product is free of defects and covers only replacing the Bone Dry Product if there is a claim on the product.

Contact

Bone Dry Products

9009 58th Pl

Kenosha, WI 53144

262-694-9748

Email: info@bonedryproducts.com